Ontario Geological Survey
Aggregate Resources Inventory Paper 57

AGGREGATE RESOURCES INVENTORY OF BIDDULPH TOWNSHIP Middlesex County SOUTHERN ONTARIO

by
Staff of the Engineering and Terrain Geology Section
Ontario Geological Survey

1982

Ontario
Ministry of Natural Resources
Hon. Alan W. Pope
Minister
W. T. Foster
Deputy Minister

© OMNR-OGS 1982

Publications of the Ontario Ministry of Natural Resources
and price list
are obtainable through the
Ontario Ministry of Natural Resources, Map Unit, Public Service Centre
Queen's Park, Toronto, Ontario
and
The Ontario Government Bookstore
880 Bay Street, Toronto, Ontario

Orders for publications should be accompanied by cheque
or money order, payable to the Treasurer of Ontario

ISSN 0708-2061
ISBN 0-7743-6004-6

This report was prepared by: Staff of the Aggregate Assessment Office, Engineering and Terrain Geology Section of the Ontario Geological Survey, Ontario Ministry of Natural Resources, 77 Grenville Street, Toronto, M5S 1B3, Telephone (416) 965-1182.

Project Supervisor: Dale W. Scott
Text Prepared by: E. Garnet
Compilation and Drafting by: Staff of the Aggregate Assessment Office

The Mineral Resources Staff of Aylmer District and Southwestern Region of the Ministry of Natural Resources assisted in the collection of data, field checking and review of this report.

Parts of this publication may be quoted if credit is given to the Ontario Ministry of Natural Resources, Ontario Geological Survey. It is recommended that reference to this report be made in the following form:

Ontario Geological Survey
1982: Aggregate Resources Inventory of Biddulph Township, Middlesex County; Ontario Geological Survey, Aggregate Resources Inventory Paper 57, 31 p., 6 tables, 3 maps, scale 1:50 000.

Every possible effort is made to ensure the accuracy of the information contained in this report, but the Ministry of Natural Resources does not assume any liability for errors that may occur. Source references are included in the report and users may wish to verify critical information.

500-81-Carswell

CONTENTS

Page

Abstract v
Introduction 1
Part I - Inventory Methods 2
Field and Office Methods 2
Resource Tonnage Calculation Techniques 2
Sand and Gravel Resources 2
Bedrock Resources 3
Units and Definitions 3
Part II - Data Presentation and Interpretation 4
Map 1 Distribution of Sand and Gravel Deposits 4
Map 2 Selected Sand and Gravel Resource Areas 4
Site Specific Criteria 5
Deposit Size 5
Aggregate Quality 5
Location and Setting 6
Regional Considerations 6
Map 3 Bedrock Resources 7
Selection Criteria 7
Selected Resource Areas 7
Part III - Assessment of Aggregate Resources in Biddulph Township 9
Location and Population 9
Physiography and Surficial Geology 9
Extractive Activity 10
Selected Sand and Gravel Resource Areas 10
Selected Sand and Gravel Resource Area 1 10
Selected Sand and Gravel Resource Area 2 11
Clay Resources 11
Bedrock Geology 12
Summary 12
References 19
Appendix A - Suggested Additional Reading 21
Appendix B - Glossary 22
Appendix C - Geology of Sand and Gravel Deposits 25
Appendix D - Geology of Bedrock Deposits 28

TABLES

1 - Total Sand and Gravel Resources, Biddulph Township 13
2 - Sand and Gravel Pits, Biddulph Township 14
3 - Selected Sand and Gravel Resource Areas, Biddulph Township 15
4 - Total Identified Bedrock Resources, Biddulph Township 16
5 - Quarries, Biddulph Township 17
6 - Selected Bedrock Resource Areas, Biddulph Township 18

FIGURES

1 - Key Map Showing Location of Biddulph Township v
2 - Bedrock Geology of Southern Ontario 28

MAPS
(back pocket)

1 - Distribution of Sand and Gravel Deposits, Biddulph Township, Scale 1:50 000.
2 - Selected Sand and Gravel Resource Areas, Biddulph Township, Scale 1:50 000.
3 - Bedrock Resources, Biddulph Township, Scale 1:50 000.

ABSTRACT



Figure 1 - Key Map Showing the Location of Biddulph Township, Scale 1:1 800 000.

This report includes both an inventory and evaluation of sand and gravel as well as bedrock resources in Biddulph Township. The report is part of the Aggregate Resources Inventory Program for townships and municipalities designated under The Pits and Quarries Control Act, 1971.

Data analysis has resulted in the selection of two sand and gravel deposits for possible resource protection in Biddulph Township. The Selected Sand and Gravel Resource Areas occupy 120 acres (49 ha), exclusive of licenced properties. An estimated 53 acres (21 ha) are currently available for extraction, containing approximately 3 million tons (3 million tonnes) of granular material. The parts of the Selected Areas which are available for extraction represent 8 percent of the township's total sand and gravel resources and 20 percent of the resource tonnage.

Selected Sand and Gravel Resource Areas 1 and 2 are located in outwash deposits of former meltwater channels. Total resources are approximately 2 million tons (2 million tonnes) and 1 million tons (1 million tonnes), respectively. The aggregate is acceptable for a variety of granular base course and hot-laid asphaltic products.

The surficial deposits of Biddulph Township are underlain by limestone of the Dundee Formation. Although the formation is suitable for crushed stone and the manufacture of portland cement, the thickness of the drift cover in Biddulph Township prohibits extraction.

Selected Resource Areas are not intended to be permanent, single land use units which must be incorporated in an official planning document. They represent areas in which a major resource is known to exist. Such Resource Areas may be reserved wholly or partially for extractive development and/or resource protection within the context of the official plan.

AGGREGATE RESOURCES INVENTORY OF BIDDULPH TOWNSHIP[1]

BY
STAFF OF THE ENGINEERING
AND TERRAIN GEOLOGY SECTION

INTRODUCTION

Mineral aggregates, which include bedrock-derived crushed stone as well as naturally formed sand and gravel, constitute the major raw material in Ontario's road-building and construction industries. Very large amounts of these materials are used each year throughout the Province. For example, in 1979, the total tonnage of mineral aggregates extracted was 144 million tons (131 million tonnes), greater than that of any other metallic or nonmetallic commodity mined in the Province (Ontario Ministry of Natural Resources 1980).

Although mineral aggregate deposits are plentiful in southern Ontario, they are fixed-location, nonrenewable resources which can be exploited only in those areas where they occur. Mineral aggregates are characterized by their high bulk and low unit value so that the economic value of a deposit is a function of its proximity to a market area as well as its quality and size. The potential for extractive development is usually greatest in urban fringe areas where land use competition is extreme. For these reasons the availability of adequate resources for future development is now being threatened in some areas.

Comprehensive planning and resource management strategies are required to make the best use of available resources, especially in those areas experiencing rapid development. Such strategies must be based on a sound knowledge of the total mineral aggregate resource base at both local and regional levels. The purpose of the Aggregate Resources Inventory is to provide the basic geological information required to include potential mineral aggregate resource areas in planning strategies and official plans. The reports should form the basis for discussion on those areas best suited for possible extraction. The aim is to assist decision-makers in protecting the public well-being by ensuring that adequate resources of mineral aggregate remain available for future use.

This report is a technical background document, based for the most part on geological information and interpretation. It has been designed as a component of the total planning process and should be used in conjunction with other planning considerations, to ensure the best use of a municipality's resources.

The report includes an assessment of sand, gravel and crushed bedrock. The most recent information available has been used to prepare the reports. As new information becomes available, revisions may be necessary.

[1] Manuscript accepted for publication by Chief Engineering and Terrain Geology Section, March 15, 1982. This paper is published with the permission of E.G. Pye, Director, Ontario Geological Survey.

PART I - INVENTORY METHODS

FIELD AND OFFICE METHODS

The methods used to prepare the report primarily involve the interpretation of published geological data such as bedrock and surficial geology maps and reports (see References). Wherever possible, field examination of potential resource areas was also undertaken to confirm interpretations made in the office. Field methods included the examination of natural and man-made exposures of granular material. Most observations were made at quarries and sand and gravel pits located from records held by the Ontario Ministry of Transportation and Communications, the Ontario Geological Survey, and by Regional and District Offices of the Ontario Ministry of Natural Resources. Observations made at pit sites included estimates of the total face height and the proportion of gravel- and sand-size fragments in the deposit. Observations were also made of the shape and lithology of the particles. These characteristics are important in estimating the quality and quantity of the aggregate. In areas of limited exposure, test pitting, soil probing and hand-augering techniques were used to assess subsurface materials. Air photos at various scales were used to determine the continuity of deposits, especially in areas of limited subsurface information.

In the office, the pit data were supplemented by information on file with the Engineering Materials Office of the Ontario Ministry of Transportation and Communications. Data contained in these files include field estimates of the depth, composition and "workability" of deposits as well as laboratory analyses of the physical properties and chemical suitability of the aggregate. Information concerning the development history of the pits and acceptable uses of the aggregate is also recorded. The location, size, and depth of extraction of pits licenced under The Pits and Quarries Control Act, 1971 were obtained from records held by Regional and District Offices of the Ontario Ministry of Natural Resources. The cooperation of the above named groups in the compilation of inventory data is gratefully acknowledged.

Water well records, held by the Ontario Ministry of the Environment, were used in some areas to corroborate thickness estimates, or to indicate the presence of buried granular material. These records were used only in conjunction with other evidence. Topographic maps of the National Topographic System, at a scale of 1:50 000, were used as a compilation base for the field and office data. The information was then transferred to a township base map, also at a scale of 1:50 000, prepared by the Cartography Section of the Lands and Waters Group, Ontario Ministry of Natural Resources, for presentation in the report.

RESOURCE TONNAGE CALCULATION TECHNIQUES

SAND AND GRAVEL RESOURCES

Once the interpretative boundaries of the aggregate units have been drawn, quantitative estimates of the possible resources available can be made. Generally, the volume of a deposit can be calculated if its areal extent and average thickness are known or can be estimated. The computation methods used are as follows: First, the area of the deposit, as outlined on the final base map, is calculated in acres. The thickness values used are an approximation of the deposit thickness, based on the face heights of pits developed in the deposit or on subsurface data such as water well logs. Original tonnage values can then be calculated by multiplying the volume of the deposit by 2500 (the density factor). This factor is approximately the number of tons in a one-foot thick layer of sand and gravel, one acre in extent, assuming an average density of 110 pounds per cubic foot.

Tonnage = Area x Thickness x Density Factor

Tonnage calculated in this manner must be considered only as an estimate. Furthermore, such tonnages represent amounts that existed prior to any extraction of material (i.e. original tonnage) (Table 1, Column 4).

The Selected Sand and Gravel Resource Areas in Table 3 represent only those parts of the deposit lying outside licenced areas (Column 2).

Two successive subtractions are made from the unlicenced area. Column 3 accounts for the number of acres unavailable due to the presence of permanent cultural features and their associated setback requirements. Column 4 accounts for those areas lying outside of licenced properties that have previously been extracted (e.g. wayside pits are included in this cateogry). The remaining figure is the area of the deposit currently available for extraction (Column 5). The available area is then multiplied by the estimated deposit thickness and the density factor (Column 5 x Column 6 x 2500) to give an estimate of the sand and gravel tonnage presently available for extractive development and/or resource protection.

BEDROCK RESOURCES

The method used to calculate resources of bedrock-derived aggregate is much the same as that described above. The areal extent of favourable bedrock formations overlain by less than 50 feet (15 m) of unconsolidated overburden is determined from bedrock geology maps, drift thickness and bedrock topography maps and from the interpretation of water well records. The measured extent of such areas is then multiplied by the estimated workable thickness of the formation, based on stratigraphic analyses and on estimates of existing quarry faces in the unit. In some cases a standardized estimate of a workable thickness of 60 feet (18 m) is used. Volume estimates are then multiplied by 3600 (the estimated weight in tons of a one-foot thick section of dolostone, one acre in extent, assuming a bulk density of 165 pounds per cubic foot).

Resources of sandstone are calculated using a bulk density estimate of 146 pounds per cubic foot or approximately 3200 tons per acre. Shale resources are calculated on the basis of a bulk density estimate of 150 pounds per cubic foot.

UNITS AND DEFINITIONS

Although most of the measurements and other primary data available for resource tonnage calculations are given in Imperial units, Metric units have also been given in the text and on the tables which accompny the report. The Metric equivalent of the data is shown in brackets after or directly below the corresponding Imperial figures. Data are generally rounded off in accordance with the Ontario Metric Practice Guide (Metric Committee 1975).

The tonnage estimates made for sand and gravel as well as bedrock-derived aggregates are termed possible resources in accordance with terminology of the Ontario Resource Classification Scheme (Robertson 1975, p. 7) and with the Association of Professional Engineers of Ontario (1976) (see Glossary, Appendix B).

PART II - DATA PRESENTATION AND INTERPRETATION

Three maps, each portraying a different aspect of the aggregate resources in the municipality, accompany the report. Map 1, "Distribution of Sand and Gravel Deposits", gives a comprehensive inventory of the sand and gravel resources in the report area. Map 2, "Selected Sand and Gravel Resource Areas", shows those deposits which are considered to represent the largest and/or highest quality resources in the area. Map 3, "Bedrock Resources", shows the distribution of bedrock formations, the distribution of overlying unconsolidated sediments, and identifies the Selected Bedrock Resource Areas.

MAP 1: DISTRIBUTION OF SAND AND GRAVEL DEPOSITS

Map 1 is derived directly from the existing surficial geology maps of the area or from air photo interpretation where surficial mapping is incomplete. It shows the extent of sand and gravel deposits within the study area and serves as a base for the calculation of the total sand and gravel resources.

Map 1 presents a summary of all available information related to the quantity and quality of aggregate contained in all the known aggregate deposits in the study area. Much of this information is contained in the symbol which identifies each deposit. The Deposit Symbol is similar to those used in soil mapping and land classification systems commonly in use in North America. The components of the symbol indicate the gravel content, thickness of material, origin (type), and quality limitations for a given deposit. These components are illustrated by the following example:



This symbol identifies an outwash deposit 10 to 20 feet (3 to 6 m) thick containing more than 35 percent gravel. Excess fines may limit uses of the aggregate in the deposit.

The "gravel content" and "thickness class" are basic criteria for distinguishing different deposits. The "gravel content" symbol is an upper case "S" or "G". The "S" indicates that the deposit is generally "sandy" and that gravel-sized aggregate makes up less than 35 percent of the whole deposit. "G" indicates that the aggregate probably contains more than 35 percent gravel.

The "thickness class" indicates a depth range which is related to the potential resource tonnage for each deposit. Four thickness class divisions have been established as shown in the legend for Map 1.

Two smaller sets of letters, divided from each other by a horizontal line, follow the thickness class number. The upper series of letters identify the geologic deposit type (the types are summarized with respect to their main geologic and extractive characteristics in Appendix C) and the lower series of letters identify the main quality limitations that may be present in the deposit as discussed in the next section.

The other information presented on Map 1 is designed to give an indication of the present level of extractive activity in the study area. Those areas which are licenced for extraction under The Pits and Quarries Control Act, 1971 are shown by a solid outline and identified by a number which refers to the pit descriptions in Table 2. Each description notes the owner, location and licenced acreage of the pit, as well as the estimated face height and percentage gravel. A number of unlicenced pits (abandoned pits or wayside pits operating under authority of a permit) are also identified and numbered on Map 1 and described in Table 2.

MAP 2: SELECTED SAND AND GRAVEL RESOURCE AREAS

Map 2 is an interpretative map derived from an evaluation of the deposits shown on Map 1. The deposits identified on Map 2 are those which are considered to be important in ensuring an adequate resource base for the future.

All the selected sand and gravel resource areas are first delineated by geological boundaries and then classified into three levels of significance: primary; secondary; and tertiary. These areas are identified on Map 2 by different shading patterns.

Each area of primary significance is assessed as to its probable relative value as a resource in the municipality and is given a deposit number which denotes its ranking order. All such deposits are shown by a medium-grey tone on Map 2.

Selected Aggregate Resource Areas of primary significance are not permanent, single land use units which must be incorporated in an official planning document. They represent areas in which a major resource is known to exist. Such resource areas may be reserved wholly or partially for extractive development and/or resource protection within the context of the official plan.

Deposits of secondary significance are not ranked numerically in this report, but are indicated by a light grey tone on Map 2. Such deposits are believed to contain significant amounts of sand and gravel. Although deposits of secondary significance are not considered to be the "best" resource areas in a municipality, they may contain large quantities of sand and gravel and should be considered an integral component of the aggregate supply of the municipality.

Areas of tertiary significance are indicated on the map by a dashed line but have no grey tone. They are neither rated nor considered to be important resource areas because of their low available resources, or because of possible difficulties in extraction. Such areas may be useful for local needs but are unlikely to support large-scale development.

The process by which deposits are evaluated and selected involves the consideration of two sets of criteria. The main selection criteria are site specific, related to the characteristics of individual deposits. Factors such as deposit size, aggregate quality, and deposit location and setting are considered in the selection of those deposits best suited for extraction development. A second set of criteria involves the assessment of local aggregate resources in relation to the quality, quantity, and distribution of resources in the region in which the municipality is located. The intent of such a process of evaluation is to ensure the continuing availability of sufficient resources to meet possible future demands.

SITE SPECIFIC CRITERIA

DEPOSIT SIZE

Ideally, selected deposits should contain available sand and gravel resources large enough to support a commercial pit operation using a stationary or portable processing plant. In practice, much smaller deposits may be of significant value depending on the overall reserves in the rest of the municipality. Generally, deposits in Class 1, i.e. those thicker than 20 feet (6m) and containing more than 35 percent crushable gravel are considered to be most favourable for commercial development. Thinner deposits may be valuable in municipalities with low total resources.

AGGREGATE QUALITY

The limitations of natural aggregates for various uses result from variations in the lithology of the particles composing the deposit, and from variations in the size distribution of these particles.

Four indicators of the quality of aggregate may be included in the symbol for each deposit on Map 1. They are: gravel content (G or S); fines (C); oversize (O), and lithology (L).

Three of the indicators deal with grain size distribution. The "gravel content", (G or S), indicates the suitability of aggregate for various uses. Deposits containing more than 35 percent crushable gravel are considered to be favourable extractive sites, since this content is the minimum from which crushed products can be economically produced.

Exesss "fines" or high silt and clay content may severely limit the potential use of an aggregate. Fines content in excess of 10 percent may impede drainage in road sub-base aggregate and render it more susceptible to the effects of frost action. In asphalt aggregate, excess fines hinder the bonding of particles. Deposits known to have a high fine content are indicated by a "C" in the quality portion of the Deposit Symbol.

Deposits containing more than 20 percent "oversize" particles (those greater than 4 inches (10 cm) in diameter) may also have use limitations. The oversize component is unacceptable for all concrete aggregate and for road-building

aggregate, so must be either crushed or removed during processing. Deposits known to have an appreciable oversize component are indicated by an "O" in the quality portion of the Deposit Symbol.

The other indicator of the quality of an aggregate is "lithology". Just as the unique physical and chemical properties of bedrock formations determine their value for use as crushed rock, so do various lithologies of particles in a sand and gravel deposit determine its suitability for various uses. The presence of objectionable lithologies such as chert, siltstone, and shale, even in relatively small amounts, can result in a reduction in the quality of an aggregate, especially for high-quality uses. Deposits known to contain objectionable lithologies are indicated by an "L" in the quality component of the Deposit Symbol.

If the Deposit Symbol indicates either "C" "O" or "L" or any combination, the quality of the deposit is considered to be reduced for some uses of the aggregate. No attempt has been made to quantify the degree of limitation imposed. Assessment of the four indicators is made from published data, from data contained in files of the Ontario Ministry of Transportation and Communications and the Engineering and Terrain Geology Section of the Ontario Geological Survey, and from field observations. The Engineering Materials Office of the Ontario Ministry of Transportation and Communications has recently compiled a detailed assessment of aggregate suitability for selected areas in southern Ontario. This material has been consulted extensively in preparation of the inventory reports.

LOCATION AND SETTING

The location and setting of a resource area has a direct influence on its value for possible extraction. The evaluation of a deposit's setting is made on the basis of those natural and man-made features which may limit or prohibit extractive development.

First, the physical context of the deposit is considered. Deposits with some physical constraint on extractive development, such as thick overburden or high water table, are less valuable resource areas because of the difficulties involved in resource recovery. Second, permanent man-made features, such as roads, railways, powerlines, and housing developments, which are built on a deposit, may prohibit its extraction. The constraining effect of legally required setbacks surrounding such features is included in the evaluation. A quantitative assessment of these constraints can be made by measurement of their areal extent directly from the topographic maps. The area rendered unavailable by these features is shown for each resource area in Table 3.

The assessment of sand and gravel deposits and bedrock resource areas with respect to local land use and to private land ownership is an important component of the general evaluation process. These aspects of the evaluation process are not considered further in this report but readers are encouraged to discuss them with personnel of the Ontario Ministry of Natural Resources' District Office.

REGIONAL CONSIDERATIONS

In selecting sufficient areas for resource development, it is important to assess both the local and the regional resource base, and to forecast future production and demand patterns.

Some appreciation of future aggregate requirements in an area may be gained by assessing its present production levels and by forecasting future production trends. Such an approach is based on the assumptions that production levels in an area closely reflect the demand and that the present production "market share" of an area will remain at roughly the same level.

The aggregate resources in the region surrounding a municipality should be assessed in order to properly evaluate specific resource areas and to adopt optimum resource management plans. For example, a municipality that has large resources in comparison to its surrounding region constitutes a regionally significant resource area. Municipalities with high resources in proximity to large demand centres, such as metropolitan areas, are special cases.

Although an appreciation of the regional context is required to develop comprehensive resource management techniques, such detailed evaluation is beyond the scope of this report. The selection of resource areas made in this study is based primarily on geological

data or on considerations outlined in preceding sections.

MAP 3: BEDROCK RESOURCES

Map 3 is an interpretative map derived from bedrock geology, bedrock topography, drift thickness maps, water well data from the Ontario Ministry of the Environment, oil and gas well data from the Petroleum Resources Section (Ontario Ministry of Natural Resources), and from geotechnical well data from various sources. Map 3 is based on concepts similar to those outlined for Maps 1 and 2, but displays both the inventory and evaluation on the one map.

The geological boundaries of the labelled bedrock units are shown by a dashed line. Isolated outcrops are indicated by an "X". Three sets of contour lines delineate areas of less than 3 feet (1 m) of drift, areas of 3 to 25 feet (1 to 8 m) of drift, and areas of 25 to 50 feet (8 to 15 m) of drift. The extent of the areas of thin drift are shown by three tones. The darkest tone indicates areas where bedrock outcrops or is within 3 feet (1 m) of the ground surface. These areas constitute potential resource areas of primary significance due to their easy access. The medium tone indicates areas where drift cover is up to 25 feet (8 m) thick. Quarrying is possible in this depth of overburden and these also represent potential resource areas. The lightest tone indicates bedrock areas overlain by 25 to 50 feet (8 to 15 m) of overburden. These latter areas constitute resources which have extractive value only in specific circumstances. Outside of these delineated areas the bedrock can be assumed to be covered by more than 50 feet (15 m) of overburden, a depth generally considered to be too great to allow economic extraction (unless part of the overburden is composed of economically attractive sand and gravel deposits).

Other inventory information presented on Map 3 is designed to give an indication of the present level of extractive activity in the municipality. Those areas which are licenced for extraction under The Pits and Quarries Control Act, 1971 are shown by a solid outline and identified by a number which refers to the quarry descriptions in Table 5. Each description notes the owner, location, and licenced acreage of the quarry and an estimate of face height. Unlicenced quarries (abandoned quarries or wayside quarries operating under authority of a permit) are also identified and numbered on Map 3 and described in Table 5. One additional symbol appears on the map: an open dot indicates the location of a selected well which penetrates bedrock. The overburden thickness is shown in feet beside the open dot.

SELECTION CRITERIA

Criteria equivalent to those for sand and gravel deposits are used to select bedrock areas most favourable for extractive development.

The evaluation of bedrock resources is made primarily on the basis of performance and suitability data established by laboratory testing at the Ontario Ministry of Transportation and Communications. The main characteristics and use of the bedrock formations found in southern Ontario are summarized in Appendix D.

Deposit "size" is related directly to the areal extent of thin drift cover overlying favourable bedrock formations of sufficient thickness to support quarry operations. Since vertical and lateral variations in bedrock units are much more gradual than in sand and gravel deposits, the quality and quantity of the resource is usually consistent over large areas.

Quality of the aggregate derived from specific bedrock units is established by the performance standards previously mentioned. Location and setting criteria and regional considerations are identical to those for sand and gravel deposits.

SELECTED RESOURCE AREAS

Selection of bedrock resource areas has been restricted to a single level of significance. Three factors support this approach. Quality and quantity variations are gradual. The areal extent of a given quarry operation is much smaller than that of a sand and gravel pit producing an equivalent tonnage of material. Since crushed bedrock has a higher unit value than sand and gravel, longer haul distances can be considered. These factors allow the identification of alternative sites having similar development potential. The wider range of possible resource areas allows greater flexibility in locating quarry operations away from areas of intensive land use competition. The Selected Areas are shown on Map 3 by a line pattern and the calculated available tonnages are given in Table 6.

Selected Bedrock Resource Areas shown on Map 3 are not permanent, single land use units which must be incorporated in an official planning document. They represent areas in which a major bedrock resource is known to exist. Such a resource area may be reserved wholly or partially for extractive development and/or resource protection within the context of the official plan.

PART III - ASSESSMENT OF AGGREGATE RESOURCES IN BIDDULPH TOWNSHIP

LOCATION AND POPULATION

Biddulph Township occupies an area of 41,011 acres (16 597 ha) in northern Middlesex County. The township is shown on the Lucan (40 P/3) and St. Marys (40 P/6) map sheets of the National Topographic System at a scale of 1:50 000. The surrounding townships are Blanshard to the east, Usborne to the northeast, Stephen to the northwest, McGillivray to the west, and London to the south.

In 1980, Biddulph Township had a population of 2324, representing a 10 percent increase over the 1973 population (Ontario Ministry of Intergovernmental Affairs 1981; Ontario Ministry of Treasury, Economics and Intergovernmental Affairs 1974). The Village of Lucan, located in the southwest corner of the township, is a locally important growth centre. The population of Lucan grew by over 30 percent, from 1213 in 1973 to 1579 in 1980 (Ontario Ministry of Intergovernmental Affairs 1981; Ontario Ministry of Treasury, Economics and Intergovernmental Affairs 1974). Lucan's rate of growth has been at the expense of the surrounding rural community. However, in the coming years, smaller centres, such as Clandeboye and Granton, are planned to accommodate much of the township's projected 2 percent per annum growth (Ontario Ministry of Housing 1977). As a result, access to mineral aggregates for use in road building and construction may become an important issue.

Access to aggregate deposits within the township is provided by gravel-surfaced township roads, paved county roads, King's Highways 4, 7, 23, and 401, the latter highway being located approximately 20 miles (32 km) to the south. In addition, a line of the Canadian National Railways crosses the southern part of the township, serving Lucan and Granton.

PHYSIOGRAPHY AND SURFICIAL GEOLOGY

Biddulph Township has a flat to gently rolling land surface dissected by the Little Ausable River and its tributaries and the headwaters of the Medway River. The most noticeable topographic feature is the valley of the Little Ausable River which attains a depth of 75 feet (23 m) where it crosses Highway 4, south of Clandeboye. The physiography of the area and land use activities are further discussed by Chapman and Putnam (1966). The reader is specifically referred to descriptions of two physiographic regions: the Stratford Till Plain (pp. 210-214) and the Horseshoe Moraines (pp. 198-203).

The current landscape and the distribution of surficial materials are a result of glacial events which occurred mainly during the Port Bruce Stadial of the Late Wisconsinan, approximately 15 000 to 14 000 years ago. Major advances from an ice lobe located in the Lake Huron basin were responsible for the township's surface till — the Rannoch Till — a moderately stony, silt to clay silt till (Sado 1980). The fine-grained nature of this material makes it unsuitable for any granular use.

The Seaforth, Mitchell and Lucan moraines trend across the township in a southwesterly direction and are associated with the Rannoch Till. The moraines have "knob and kettle" topography and are overlain by a considerable thickness of this fine till. Zones of gravelly material may be found at depth. The Seaforth Moraine, in particular, has gravelly sediments exposed at its core by the Little Ausable River which breaches the moraine south of Clandeboye. These buried deposits may, on further exploration, prove to be useful sources of construction aggregate (E.V. Sado, personal communication, 1980).

The surface of the till plain has been modified in places by lacustrine sediments deposited in glacial lakes and ponds formed during the retreat of the Huron lobe. The sediments consist of laminated fine gravel, sand, silt, and clay. A low, flat plain at Elginfield is representative of a small glacial lake which was formed between the confining ridges of the Lucan and Mitchell moraines (Sado 1980). The resultant deposit is an excellent source of clay for the brick and tile industry.

Meltwater channels were incised into the surface throughout the various stages of glacial retreat. In Biddulph Township, these channels contain outwash terraces of a fairly limited

extent. The material ranges from well sorted, flat-lying beds of fine sand to bouldery gravel. An important meltwater channel is now occupied by Medway Creek and extends into London Township to the south. The sandy outwash material deposited in this channel is acceptable for a variety of aggregate uses. There are also deposits of sand and gravel in an older meltwater channel flanking the eastern side of the Seaforth Moraine as well as scattered along the Little Ausable River. The former deposits are overlain by thick layers of lacustrine silt.

Deposits of ice-contact stratified drift are found within and off the flanks of the Seaforth, Lucan and Mitchell moraines. Materials in the ice-contact features are extremely variable, having been formed in close proximity to the melting ice. The sand and gravel in these deposits are usually capped by till.

Glacial activity after the Port Bruce Stadial has been of minor importance. During the recent past, the sand, silt, and gravel deposited along fluvial channels are of particular note. The floodplain alluvium of the Little Ausable River, for example, is predominantly silty, but may contain some poorly stratified sand and gravel (Sado and Vagners 1975).

EXTRACTIVE ACTIVITY

A total of twelve sand and gravel pits were identified in Biddulph Township, including several that are overgrown and currently inactive. At present, five of the pits are licenced to operate under The Pits and Quarries Control Act, 1971. The licenced properties have a total area of 156.2 acres (63.2 ha). Three are located in outwash deposits along the Little Ausable River; one is located in a small ice-contact deposit to the northeast of Lucan; and one encompasses a small area of ice-contact stratified drift on the flanks of the Seaforth Moraine, north of Clandeboye. There has been little recent active extraction and the pits are all partly to completely overgrown.

Production figures for licenced sources have been compiled annually by the Aylmer District Office of the Ontario Ministry of Natural Resources since designation of the township in 1975. The average annual production in the township between 1975 and 1978 was 44,572 tons (40 436 tonnes).

SELECTED SAND AND GRAVEL RESOURCE AREAS

Map 1 indicates the deposits which contain granular material in Biddulph Township. The total extent of these deposits is approximately 650 acres (265 ha), representing an original tonnage of 15 million tons (14 million tonnes). Many of these potential resources have limited value for reasons of deposit size, thickness or quality of the material. Consequently, only the most significant sources are suggested for possible protection.

The sources of primary value are all related in origin to glacial meltwater channels. One outwash deposit along the Medway Creek and a second along the Little Ausable River contain good-quality aggregate to a depth of about 20 to 25 feet (6 to 8 m). These two sources have a combined area of 120 acres (49 ha), exclusive of licenced properties. Fifty-three acres (21 ha) are currently available for extraction. Total aggregate resources are estimated to be 3 million tons (3 million tonnes) or 20 percent of the township's total tonnage.

The remaining outwash, ice-contact, and alluvial deposits are relatively less important. Although these are not the best sources, they should be considered as part of the township's aggregate supply.

Of additional interest, is a former glacial lake clay deposit, approximately 20 feet (6 m) deep, located to the northeast of Elginfield. The deposit is clearly not suitable for aggregate, but may be a useful source of clay for the brick and tile industry.

SELECTED SAND AND GRAVEL RESOURCE AREA 1

Sand and Gravel Resource Area 1 is a sandy outwash deposit of approximately 90 acres (36 ha). The deposit is part of a former meltwater channel now occupied by Medway Creek. The channel continues southwards into London Township where resource protection at the primary level has also been suggested.

Data obtained from the Ontario Ministry of Transportation and Communications identify the deposit as a source of crushable gravel. Field investigation of a wayside pit (pit no. 12) revealed a gravel content varying from 30 to 50

percent. An 8- to 10-foot (2 to 3 m) face at this site shows medium to coarse sand underlain by layers of poorly sorted, fine to medium gravel with a coarse sand matrix. Examination of former extractive sites in the London Township portion of the deposit suggest that about 20 to 30 feet (6 to 9 m) of gravelly sand may be available. However, the hummocky nature of the deposit in Biddulph Township may indicate variability in both depth and composition.

Deike (1976) states that the material in pit no. 12 is acceptable for Granular Base Course (G.B.C.) A, B, and C, and hot-laid asphalt stone. Silty sections in the sand fraction, however, will be a limiting factor in the production of hot-laid asphalt sand.

Resource Area 1 has 33 acres (13 ha) currently available for extraction. Assuming a deposit thickness of 25 feet (8 m), sand and gravel resources are estimated to be 2 million tons (2 million tonnes). The high water table, as evidenced by ponding in pit no. 12, may make extraction difficult.

SELECTED SAND AND GRAVEL RESOURCE AREA 2

Sand and Gravel Resource Area 2 is an outwash gravel deposit of approximately 65 acres (26 ha) located along a bend in the Little Ausable River, south of Clandeboye. The outwash materials are, in fact, older alluvium which was deposited in the meltwater channel during the melting of the Huron ice lobe.

Two licenced properties (pit nos. 4 and 5) are located in the Area. These pits are largely overgrown and, therefore, difficult to evaluate. An exposed face in pit no. 4 reveals 1 to 2 feet (0.3 to 0.6 m) of medium to coarse sand underlain by 5 to 8 feet (2 m) of coarse gravel mixed with coarse sand. The gravel content is approximately 60 to 70 percent with a high oversize component. The material is poorly sorted and the bedding is indistinct. Faces in pit no. 5 are sloughed and overgrown and the property is largely depleted. Office analysis and field comparison with pit no. 4 suggest that the gravel content in pit no. 5 was much lower — i.e. in the order of 30 to 50 percent. However, several large blocks of poorly sorted, fine to coarse gravel cemented with calcium carbonate are present on the pit floor. Cementation may be common in other areas of the deposit.

Deike (1976, p. 9) comments that "Materials found in the Little Ausable River valley are of very high quality and are suitable for all road base course, concrete and hot mix uses with the exception of H.L. 1." The sand tends to be coarse and dirty for hot-laid asphalt sand and occasional chert concentrations may be a problem unless all particles finer than 1 inch (2.5 cm) are screened out and the larger fraction is crushed. Areas containing cemented aggregate may be less acceptable.

Resource Area 2 has an extent of 32 acres (13 ha), exclusive of the licenced areas. Setback allowances reduce the area currently available to 20 acres (8 ha) and there has been no previous extraction in wayside pits. Assuming a deposit thickness of 20 feet (6 m), sand and gravel resources are approximately 1 million tons (1 million tonnes). Additional resources of similar material are buried below the till of the Seaforth Moraine to the west of pit no. 4 (E.V. Sado, personal communication, 1980). Consequently, the tonnage value for this area is likely to be an underestimate.

CLAY RESOURCES

Meltwaters issuing from the Huron ice lobe laid down stratified deposits of clay and silt in the quiet waters of glacial lakes. One such clay deposit is located near Elginfield. Guillet (1967, p. 187) notes that a well log at Elginfield shows 40 feet (12 m) of silty calcareous clay. Three feet (1 m) of this olive grey clay is visible in a water-filled, licenced clay pit in London Township to the south. The clay has chemical, mineralogical, and ceramic properties which make it suitable for the manufacture of brick and tile. A brick and tile plant in London Township uses clay from this deposit.

The clay deposit in Biddulph Township has similar properties and may prove to be a valuable resource in the future. There is a great demand in southwestern Ontario for drainage tile to improve the predominantly heavy clay soils. Despite the availability of plastic pipes, Guillet (1977, p. 71) states that there are ". . . signs of resurgence in clay tile-making as a result of the sharply increasing cost of plastics related to the rising prices of all petroleum products."

BEDROCK GEOLOGY

Surficial material in Biddulph Township is underlain by bedrock of the Dundee Formation. This formation consists of 60 to 160 feet (18 to 49 m) of light brown, medium-grained limestone with some chert present (Hewitt 1972, p. 12). The limestone is quarried near St. Marys in Blanshard Township for the manufacture of portland cement. Elsewhere in southern Ontario, the formation is quarried for crushed stone.

In Biddulph Township drift thicknesses generally exceeding 100 feet (30 m) and in places 200 feet (61 m) have prohibited extraction and exploitation of the Dundee Formation.

SUMMARY

The sand and gravel deposits of Biddulph Township are the product of glacial activity during the Late Wisconsinan. The two primary resource areas are outwash deposits related to former meltwater channels. Although these resource areas are small, they contain good-quality aggregate and may be supplemented by material in the remaining deposits. An additional resource of value is a lacustrine deposit containing clay acceptable for use in brick and tile making.

Drift thickness in Biddulph Township is too great to permit extraction of the limestone from the underlying bedrock.

Enquiries regarding the Aggregate Resources Inventory of Biddulph Township should be directed to the Ontario Ministry of Natural Resources either at the Aylmer District Office, 353 Talbot Street West, Aylmer, Ontario, N5H 2S8 (Tel. (519) 773-9241) or at the Southwestern Region Geological Office, 458 Central Avenue, London, Ontario, N6B 2E5 (Tel. (519) 433-8431).

TABLE 1 | TOTAL SAND AND GRAVEL RESOURCES, BIDDULPH TOWNSHIP*

1 CLASS NO.	2 DEPOSIT TYPE (see Appendix C)	3 AREAL EXTENT Acres (Hectares)	4 ORIGINAL TONNAGE Millions of Tons (Tonnes)
SAND AND GRAVEL RESOURCES			
1	G-OW	64 (26)	3 (3)
	S-OW	88 (36)	6 (5)
3	G-IC	104 (42)	2 (2)
	G-OW	60 (24)	1 (1)
4	S-AL	315 (128)	3 (3)
	S-IC	20 (8)	<1 (<1)
		650 (265)	15 (14)
CLAY RESOURCES			
1	C-LP	780 (315)	No Estimate

* Identified deposit areas in the Village of Lucan are omitted on all tables.

N.B. Minor variations in the above table are due to rounding of data.

TABLE 2 | SAND AND GRAVEL PITS, BIDDULPH TOWNSHIP

1 NO.	2 MTC NO.	3 OWNER/OPERATOR	4 LOT	5 CON.	6 LICENCED AREAS Acres (Hectares)	7 FACE HEIGHT Feet (Metres)	8 % GRAVEL
LICENCED PITS							
1	–	Walloy Excavating Ltd.	Pt. 21	1	71.0 (28.7)	10-15 (3-5)	60-70 partly overgrown
2	–	Corbett and Young Inc.	Pt. 2	2	7.0 (2.8)	3-5 (1-2)	50-60 partly overgrown and water filled
3	–	Corbett and Young Inc.	W½ 24	8	2.2 (0.9)	8-10 (2-3)	depleted
4	–	Wilson Hodgins	Pt. 29, 30	2	63.0 (25.5)	8-10 (2-3)	60-70 partly overgrown
5	–	Corbett and Young Inc.	Pt. 30	2	13.0 (5.3)	5-8 (2)	30-50 overgrown
					156.2 (63.2)		
UNLICENCED PITS*							
6	L7-152	L. Hodgins	15	4		10-15 (3-5)	60-70 partly overgrown
7	L7-39	L. Hodgins	17	4		<10 (<3)	overgrown
8	L7-75	S. Jones	20	1		15-20 (5-6)	50-60 partly overgrown
9	L7-166	Nippa	25	2		–	overgrown and water filled
10	L7-150	W. Hodgins	25	3		15-20 (5-6)	50-60
11	L7-6	Hager	39	2		5-8 (2)	overgrown
12	L7-56	McRoberts and Neil	9	11 (S.B.C.)		8-10 (2-3)	30-50 partly overgrown

* Abandoned pits or wayside pits operating on demand under authority of a permit.

TABLE 3 | SELECTED SAND AND GRAVEL RESOURCE AREAS, BIDDULPH TOWNSHIP

1 **DEPOSIT NO.**	2 **UNLICENCED AREA** Acres (Hectares)	3 **CULTURAL SETBACKS** Acres (Hectares)	4 **EXTRACTED AREA** Acres (Hectares)	5 **AVAILABLE AREA** Acres (Hectares)	6 **ESTIMATED DEPOSIT THICKNESS** Feet (Metres)	7 **AVAILABLE AGGREGATE** Millions of Tons (Tonnes)
1	88 (36)	50 (20)	5 (2)	33 (13)	25 (8)	2 (2)
2	32 (13)	12 (5)	0 (0)	20 (8)	20 (6)	1 (1)
	120 (49)	62 (25)	5 (2)	53 (21)		3 (3)

N B. Minor variations in above table are due to rounding of data.

TABLE 4 | TOTAL IDENTIFIED BEDROCK RESOURCES, BIDDULPH TOWNSHIP

1 **DRIFT THICKNESS** Feet (Metres)	2 **FORMATION**	3 **ESTIMATED DEPOSIT THICKNESS** Feet (Metres)	4 **AREAL EXTENT** Acres (Hectares)	5 **ORIGINAL TONNAGE** Millions of Tons (Tonnes)
		– NONE –		

TABLE 5 | QUARRIES, BIDDULPH TOWNSHIP

1 NO.	2 MTC NO.	3 OWNER/OPERATOR	4 LOT	5 CON.	6 LICENCED AREA Acres (Hectares)	7 FACE HEIGHT Feet (Metres)

– NONE –

TABLE 6 | SELECTED BEDROCK RESOURCE AREAS, BIDDULPH TOWNSHIP

1 **DEPOSIT NO.**	2 **DEPTH OF OVERBURDEN** Feet (Metres)	3 **UNLICENCED AREA** Acres (Hectares)	4 **CULTURAL SETBACKS** Acres (Hectares)	5 **EXTRACTED AREA** Acres (Hectares)	6 **AVAILABLE AREA** Acres (Hectares)	7 **ESTIMATED WORKABLE THICKNESS** Feet (Metres)	8 **AVAILABLE RESOURCES** Millions of Tons (Tonnes)
– NONE –							

REFERENCES

Association of Professional Engineers of Ontario
1976: Performance Standards for Professional Engineers Advising on and Reporting on Oil, Gas and Mineral Properties; Association of Professional Engineers of Ontario, 11 p.

Chapman, L.J. and Putnam, D.F.
1966: The Physiography of Southern Ontario; Second Edition, University of Toronto Press, 386 p.

Deike, W.
1976: Mineral Aggregate Resources in the Township of Biddulph; Geotechnical Office, Ontario Ministry of Transportation and Communications, 18 p., unpublished report.

Guillet, G.R.
1967: The Clay Products Industry of Ontario; Ontario Department of Mines, Industrial Mineral Report 22, 206 p. Accompanied by Maps 2130 and 2131, scale 1:1 013 760.
1977: Clay and Shale Deposits of Ontario; Ontario Geological Survey, Mineral Deposits Circular 15, 117 p. Accompanied by Map 2358, scale 1:2 000 000.

Hewitt, D.F.
1972: Paleozoic Geology of Southern Ontario; Ontario Division of Mines, Geological Report 105, 18 p. Accompanied by Map 2254, scale 1:1 013 760.

Karrow, P.F.
1965: Bedrock Topography Series Lucan Sheet; Ontario Department of Mines, Preliminary Map P. 291, Bedrock Topography Series, scale 1:50 000.
1977: Quaternary Geology of the St. Marys Area; Ontario Division of Mines, Geoscience Report 148, 59 p. Accompanied by Map 2366, scale 1:50 000.

Karrow, P.F. and Ferguson, A.J.
1975: Bedrock Topography of the St. Marys Area; Ontario Division of Mines, Preliminary Map P. 266, Bedrock Topography Series, scale 1:50 000.

Ontario
1981: The Pits and Quarries Control Act, 1971; Revised Statutes of Ontario, 1980, Chapter 378, Queen's Printer for Ontario.

Ontario Interministerial Committee on National Standards and Specifications (Metric Committee)
1975: Metric Practice Guide; 67 p.

Ontario Ministry of Housing
1977: The Official Plan for the Township of Biddulph Planning Area; Community Planning Advisory Branch Southwestern Branch, London, Ontario.

Ontario Ministry of Intergovernmental Affairs
1981: Municipal Directory 1981; Queen's Printer for Ontario, 191 p.

Ontario Ministry of Natural Resources
1980: Statistics 1980; Ontario Ministry of Natural Resources, 122 p.

Ontario Ministry of Treasury, Economics and Intergovernmental Affairs
1974: Municipal Directory 1974; Queen's Printer for Ontario, 128 p.

Robertson, J.A.
1975: Mineral Deposit Studies, Mineral Potential Evaluation, and Regional Planning in Ontario; Ontario Division of Mines, Miscellaneous Paper 61, 42 p.

Sado, E.V.
1980: The Quaternary Stratigraphy and History of the Lucan Map Area, Southwestern Ontario; Unpublished MSc. Thesis, University of Waterloo, 146 p.

Sado, E.V. and Jones, D.
1980: Drift Thickness of the Lucan Area, Southern Ontario; Ontario Geological Survey, Preliminary Map P. 2359, Drift Thickness Series, scale 1:50 000.

Sado, E.V. and Vagners, U.J.
1975: Quaternary Geology of the Lucan Area, Southern Ontario; Ontario Division of Mines, Preliminary Map P. 1048, Geological Series, scale 1:50 000.

Sanford, B.V.
1969: Geology of the Toronto-Windsor Area, Ontario; Geological Survey of Canada, Map 1263A, scale 1:250 000.

APPENDIX A - SUGGESTED ADDITIONAL READING

American Geological Institute
1972: Glossary of Geology; Washington, D.C., 858 p.

Bauer, A.M.
1970: A Guide to Site Development and Rehabilitation of Pits and Quarries; Ontario Department of Mines and Northern Affairs, Industrial Mineral Report 33, 62 p.

Cowan, W.R.
1977: Towards the Inventory of Ontario's Mineral Aggregates; Ontario Geological Survey, Miscellaneous Paper 73, 19 p.

Fairbridge, R.W. (ed.)
1968: The Encyclopedia of Geomorphology; Encyclopedia of Earth Sciences, Vol. III, Reinhold Book Corp., N.Y., 1295 p.

Flint, R.F.
1971: Glacial and Quaternary Geology; John Wiley and Sons Inc., 892 p.

Hewitt, D.F.
1960: The Limestone Industries of Ontario; Ontario Department of Mines, Industrial Mineral Report 5, 177 p.
1964a: Building Stones of Ontario, Part I Introduction; Ontario Department of Mines, Industrial Mineral Report 14, 43 p.
1964b: Building Stones of Ontario, Part II Limestone; Ontario Department of Mines, Industrial Mineral Report 15, 41 p.
1964c: Building Stones of Ontario, Part III Marble; Ontario Department of Mines, Industrial Mineral Report 16, 89 p.
1964d: Building Stones of Ontario, Part IV Sandstone; Ontario Department of Mines, Industrial Mineral Report 17, 57 p.
1972: Paleozoic Geology of Southern Ontario; Ontario Division of Mines, Geological Report 105, 18 p.

Hewitt, D.F. and Karrow, P.F.
1963: Sand and Gravel in Southern Ontario; Ontario Department of Mines, Industrial Mineral Report 11, 151 p.

Hewitt, D.F. and Vos, M.A.
1970: Urbanization and Rehabilitation of Pits and Quarries; Ontario Department of Mines, Industrial Mineral Report 34, 21 p.

Lowe, S.B.
1980: Trees and Shrubs for the Improvement and Rehabilitation of Pits and Quarries in Ontario; Ministry of Natural Resources, 71 pg.

McLellan, A.G.; Yundt, S.E. and Dorfman, M.L.
1979: Abandoned Pits and Quarries in Ontario; Ontario Geological Survey, Ministry of Natural Resources, Miscellaneous Paper 79, 36 pg.

Ontario Mineral Aggregate Working Party
1977: A Policy for Mineral Aggregate Resource Management in Ontario; Ontario Ministry of Natural Resources, 232 p.

Ontario Ministry of Natural Resources
1975: Vegetation for the Rehabilitation of Pits and Quarries; Forest Management Branch Division of Forests, 38 p.

Peat, Marwick & Partners and
M.M. Dillon Limited
1981: Mineral Aggregate Transportation Study; Industrial Minerals Background Paper 1, 133 pg. Summary Report 26 pg.

Proctor and Redfern Ltd.
1974: Mineral Aggregate Study, Central Ontario Planning Region; Prepared for the Ontario Ministry of Natural Resources, over 100 p.

Proctor and Redfern Ltd., and Gartner Lee Associates Ltd.
1975: Mineral Aggregate Study of Part of The Eastern Ontario Region; Prepared for the Ontario Ministry of Natural Resources, about 200 p.

1977: Mineral Aggregate Study and Geological Inventory, Southwestern Region of Ontario; Prepared for the Ontario Ministry of Natural Resources, about 200 p.

APPENDIX B - GLOSSARY

ABRASION RESISTANCE

Tests such as the Los Angeles Abrasion Test are used to measure the ability of aggregate to resist crushing and pulverizing under conditions similar to those encountered in processing and use. Measuring resistance is an important component in the evaluation of the quality and prospective uses of aggregate. Hard, durable material is preferred for road building.

ABSORPTION CAPACITY

Related to the porosity of the rock types of which an aggregate is composed. Porous rocks are subject to disintegration when absorbed liquids freeze and thaw, thus decreasing the strength of the aggregate.

AGGREGATE

Any hard, inert, construction material (sand, gravel, shells, slag, crushed stone or other mineral material) used for mixing in various sized fragments with a cement or bituminous material to form concrete, mortar, etc., or used alone for road building or other construction. Synonyms include mineral aggregate and granular material.

CAMBRIAN

The first Period of the Paleozoic Era, thought to have covered the time between 570 and 500 million years ago; the Cambrian precedes the Ordovician Period.

CLAST

An individual constituent, grain, or fragment of a sediment or rock, produced by the mechanical weathering of a large rock mass. Synonyms include particle and fragment.

DELETERIOUS LITHOLOGY

A general term used to designate those rock types which are chemically or physically unsuited for use as construction or road-building aggregates. Such lithologies as chert, shale, siltstone, and sandstone may deteriorate rapidly when exposed to traffic and other environmental conditions.

DEVONIAN

A Period of the geological past thought to have covered the span of time between 395 and 345 million years ago, following the Silurian Period. Rocks formed in the Devonian Period are among the youngest found in Ontario.

DIRT

See fines.

DOLOSTONE

A carbonate sedimentary rock consisting chiefly of the mineral dolomite and containing relatively little calcite (dolostone is also known as dolomite).

DRIFT

A general term for all unconsolidated rock debris transported from one place and deposited in another; distinguished from underlying bedrock. In North America, glacial activity has been the dominant mode of transport and deposition of drift. Synonyms include overburden and surficial deposit.

DRUMLIN

A low, smoothly rounded, elongated hill, mound, or ridge composed of glacial materials. These landforms were deposited beneath an advancing ice sheet, and were shaped by its flow.

EOLIAN

Pertaining to the wind, especially with respect to landforms whose constituents were transported and deposited by wind activity. Sand dunes are an example of an eolian landform.

FINES

A general term used to describe the size fraction of an aggregate which passes (is finer than) the No. 200 mesh screen (0.074 mm). Also described informally as "dirt", these particles are in the silt- and clay-size range.

GLACIAL LOBE

A tongue-like projection from the margin of the main mass of an ice cap or ice sheet. During the Pleistocene Epoch several lobes of the Laurentide continental ice sheet occupied the Great Lakes basins. These lobes advanced and retreated numerous times during the Pleistocene, producing the complex arrangement of glacial material and landforms found in southern Ontario.

GRADATION

The proportion of material of each particle size or the frequency distribution of the various sizes which constitute a sediment. The strength, durability, permeability and stability of an aggregate depend to a great extent on its gradation. The size limits for different particles are as follows:

Boulder		>-256 mm
Gravel	cobble	64-256 mm
Gravel	pebble	4-64 mm
Gravel	granule	2-4 mm
Sand	coarse	.5-2 mm
	medium	.25-.5 mm
	fine	.074-.25 mm
Silt, clay		<.074 mm

GRANULAR BASE COURSE

Components of the pavement structure of a road, which are placed on the subgrade and are designed to provide strength, stability, and drainage, as well as support for surfacing materials. Several types have been defined: Granular Base Course A consists of crushed and processed aggregate and has relatively stringent quality standards in comparison to Granular Base Course B and C which are usually pit-run or other unprocessed aggregate.

H.L. (HOT-LAID OR ASPHALTIC AGGREGATE)

Bituminous, cemented aggregates used in the construction of pavements either as surface or bearing course (H.L. 1, 3, and 4), or as binder course (H.L. 2, 6, and 8) used to bind the surface course to the underlying granular base course.

LITHOLOGY

The description of rocks on the basis of such characteristics as color, structure, mineralogic composition, and grain size. Generally, the description of the physical character of a rock.

MELTWATER CHANNEL

A drainage way, usually terraced, produced by water flowing away from a melting glacier margin.

ORDOVICIAN

An early peiod of the Paleozoic Era thought to have covered the span of time between 500 and 435 million years ago.

PALEOZOIC ERA

One of the major divisions of the geologic time scale thought to have covered the time between 570 and 230 million years ago. The Paleozoic Era (or Ancient Life Era) is subdivided into six geologic Periods, of which only four (Cambrian, Ordovician, Silurian, and Devonian) can be recognized in southern Ontario.

PLEISTOCENE

An Epoch of the recent geological past including the time from approximately 1.8 million years ago to 7000 years ago. Much of the Pleistocene was characterized by extensive glacial activity.

POSSIBLE RESOURCE

Estimates of mineral aggregate material based largely on broad knowledge of the geologic character of the deposit and for which there are few, if any, samples of measurements. The estimates are based on assumed continuity or repetition for which there are reasonable geological indications.

SHALE

A fine-grained, sedimentary rock formed by the consolidation of clay, silt, or mud and characterized by well developed bedding planes, along which the rock breaks readily into thin layers. The term shale is also commonly used for fissile claystone, siltstone, and mudstone.

SILURIAN

An early Period of the Paleozoic Era thought to have covered the time between 435 and 395 million years ago. The Silurian follows the Ordovician Period and precedes the Devonian Period.

SOUNDNESS

The ability of the components of an aggregate to withstand the effects of various weathering processes and agents. Unsound lithologies are subject to disintegration caused by the expansion of absorbed solutions. This may seriously impair the performance of road-building and construction aggregates.

TILL

Unsorted and unstratified rock debris, deposited directly by glaciers, and ranging in size from clay to large boulders.

WISCONSINAN

Pertaining to the last glacial stage of the Pleistocene Epoch in North America. It began approximately 100 000 years ago and ended approximately 7000 years ago. The glacial deposits and landforms of southern Ontario are predominantly the result of glacial activity during the Winsconsinan Stage.

APPENDIX C - GEOLOGY OF SAND AND GRAVEL DEPOSITS

The type, distribution, and extent of sand and gravel deposits in southern Ontario are the result of extensive glacial and glacially influenced activity in Wisconsinan time during the Pleistocene Epoch, approximately 7000 to 85 000 years ago. The deposit types reflect the different depositional environments that existed during the melting and retreat of the continental ice masses, and they can readily be differentiated on the basis of their morphology, structure, and texture. The deposit types are described below.

GLACIOFLUVIAL DEPOSITS

These deposits can be divided into two broad categories: those that were formed in contact with (or in close proximity to) glacial ice, and those that were deposited by meltwaters carrying materials beyond the ice margin.

ICE-CONTACT TERRACES (ICT)

These are glaciofluvial features deposited between the glacial margin and a confining topographic high, such as the side of a valley. The structure of the deposits may be similar to that of outwash deposits, but in most cases the sorting and grading of the material is more variable and the bedding is discontinuous due to extensive slumping. The probability of locating large amounts of crushable aggregate is moderate, and extraction may be expensive due to the variability of the deposits both in terms of quality and grain-size distribution.

KAMES (K)

Kames are defined as mounds of poorly sorted sand and gravel deposited by meltwater in depressions or fissures on the ice surface or at its margin. During glacial retreat, the melting of supporting ice causes collapse of the deposits producing internal structures characterized by bedding discontinuities. The deposits consist mainly of irregularly bedded and cross-bedded, poorly sorted sand and gravel. The present forms of the deposits include single mounds, linear ridges (crevasse fillings) or complex groups of landforms. The latter are occasionally described as "undifferentiated ice-contact stratified drift" (IC) when detailed subsurface information is unavailable. Since kames commonly contain large amounts of fine-grained material and are characterized by considerable variability, there is generally a low to moderate probability of discovering large amounts of good-quality, crushable aggregate. Extractive problems encountered in these deposits are mainly the excessive variability of the aggregate and the presence of excess fines (silt- and clay-sized particles).

ESKERS (E)

Eskers are narrow, sinuous ridges of sand and gravel deposited by meltwaters flowing in tunnels within or at the base of glaciers, or in channels on the ice surface. They vary greatly in size. Many, though not all eskers consist of a central core of poorly sorted and stratified gravel characterized by a wide range in grain size. The core material is often draped on its flanks by better sorted and stratified sand and gravel. The deposits have a high probability of containing a large proportion of crushable aggregate, and since they are generally built above the surrounding ground surface, are convenient extraction sites. For these reasons esker deposits have been traditional aggregate sources throughout southern Ontario, and are significant components of the total resources of many areas.

Some planning constraints and opportunities are inherent in the nature of the deposits. Because of their linear nature, the deposits commonly extend across several property boundaries leading to unorganized extractive development at numerous small pits. On the other hand, because of their form, eskers can be easily and inexpensively extracted and are amenable to rehabilitation and sequential land use.

UNDIFFERENTIATED ICE-CONTACT STRATIFIED DRIFT (IC)

This designation may include deposits from several ice-contact, depositional environments which usually form extensive, complex landforms. It is not feasible to identify individual areas of coarse-grained material within such deposits due to their lack of continuity and grain-size variability. They are given a qualita-

tive rating based on existing pit and other subsurface data.

OUTWASH (OW)

Outwash deposits consist of sand and gravel laid down by meltwaters beyond the margin of the ice lobes. They occur as sheets or as terraced valley fills (valley trains) and may be very large in extent and thickness. Well developed outwash deposits have good horizontal bedding and are uniform in grain-size distribution. Outwash deposited near the glacier's margin is much more variable in texture and structure. The probability of locating useful crushable aggregates in outwash deposits is moderate to high depending on how much information on size, distribution and thickness is available.

ALLUVIUM (AL)

Alluvium is a general term for clay, silt, sand, gravel, or similar unconsolidated material deposited during postglacial time by a stream as sorted or semi-sorted sediment, on its bed or on its floodplain. The probability of locating large amount of crushable aggregate in alluvial deposits in low, and it has generally low value due to the presence of excess silt- and clay-sized material. There are no large postglacial alluvium deposits in Ontario.

GLACIOLACUSTRINE DEPOSITS

GLACIOLACUSTRINE BEACH DEPOSITS (LB)

These are relatively narrow, linear features formed by wave action at the shores of glacial lakes that existed at various times during the deglaciation of southern Ontario. Well developed lacustrine beaches are usually less than 20 feet (6 m) thick. The aggregate is well sorted and stratified and sand-sized material commonly predominates. The composition and size distribution of the deposit depends on the nature of the underlying material. The probability of obtaining crushable aggregate is high when the material is developed from coarse-grained materials such as a stony till, and low when developed from fine-grained materials. Beaches are relatively narrow, linear deposits, so that extractive operations are often numerous and extensive.

GLACIOLACUSTRINE DELTAS (LD)

These features were formed where streams or rivers of glacial meltwater flowed into lakes and deposited their suspended sediment. In southern Ontario such deposits tend to consist mainly of sand and abundant silt. However, in near-ice and ice-contact positions, coarse material may be present. Although deltaic deposits may be large, the probability of obtaining coarse material is generally low.

GLACIOLACUSTRINE PLAIN (LP)

The nearly level surface marking the floor of an extinct glacial lake. The sediments which form the plain are predominantly fine to medium sand, silt, and clay, and were deposited in relatively deep water. Lacustrine deposits are generally of low value as aggregate sources due to their fine grain size and lack of crushable material. In some aggregate-poor areas, lacustrine deposits may constitute valuable sources of fill and some granular base course aggregate.

GLACIAL DEPOSITS

END MORAINES (EM)

These are belts of glacial drift deposited at, and parallel to, glacier margins. They commonly consist of ice-contact stratified drift and in such instances are usually called kame moraines. Kame moraines commonly result from deposition between two glacial lobes (interlobate moraines). The probability of locating aggregates within such features is moderate to low. Exploration and development costs are high. Moraines may be very large and contain vast aggregate resources, but the location of the best resource areas within the moraine is usually poorly defined.

EOLIAN DEPOSITS

WINDBLOWN FORMS (WD)

Windblown deposits are those formed by the transport and deposition of sand by winds. The form of the deposits ranges from extensive, thin layers to well developed linear and crescentic ridges known as dunes. Most windblown deposits in southern Ontario are derived from,

and deposited on, pre-existing lacustrine sand plain deposits. Windblown sediments are almost invariably composed of fine to coarse sand and are usually well sorted. The probability of locating crushable aggregate in windblown deposits is very low.



Figure 2 - Bedrock Geology of Southern Ontario

BEDROCK SUITABLE FOR CRUSHED STONE PRODUCTS

BASS ISLANDS FORMATION (UPPER SILURIAN)

(Includes the Bertie Formation of the Niagara Peninsula) Composition: Medium- to massive-bedded, aphanitic, brown dolostone with shaly partings. Thickness: 35 to 60 feet (11-18m) near Hagersville. Uses: Quarried for crushed stone on the Niagara Peninsula at Fort Erie, Cayuga, Hagersville, and Dunville. Los Angeles Abrasion Test: 17-35% loss; Absorption: 1.4%. Shaly parts are unsuitable for aggregate due to high soundness losses.

BOBCAYGEON FORMATION (MIDDLE ORDOVICIAN)

Composition: Compact, homogeneous, medium- to thin-bedded, fine-grained limestone with some argillaceous and shaly partings. Thickness: The lower unit is 40 to 72 feet (12 to 22 m) thick in the east and the remainder of the formation is 40 feet (12 m). Uses: Quarried at Kirkfield and Marysville for crushed stone. The Bobcaygeon Formation has consistently acceptable quality for granular base course materials and concrete.

BOIS BLANC FORMATION (LOWER-MIDDLE DEVONIAN)

Composition: Brownish grey, medium-crystalline, medium- to thin-bedded, cherty limestone, commonly fossiliferous. Limestone may be silty or sandy in places. Thickness: 9 to 200 feet (3 to 61 m). Uses: Quarried at Hagersville, Cayuga, and Port Colborne for crushed stone. High chert content makes much of the material unsuitable for concrete aggregate. Los Angeles Abrasion

Test: 14-28% loss; Soundness Test: 4-10% loss; Absorption: 0.7-2.0%.

DUNDEE FORMATION (MIDDLE DEVONIAN)

Composition: Fine- to medium-crystalline, brownish grey, medium- to thick-bedded, dolomitic limestone with shaly partings, sandy layers, and chert in some areas. Thickness: 60 to 160 feet (18 to 49 m). Uses: Quarried near Port Dover and Pelee Island for crushed stone. Used at St. Marys for portland cement. Los Angeles Abrasion Test: 22-32% loss; Absorption: 0-4%.

GULL RIVER FORMATION (MIDDLE ORDOVICIAN)

Composition: Member A: thin- to thick-bedded, interbedded, grey argillaceous limestone and buff to green dolostone with a maximum thickness of 60 feet (18 m). Members B and C are dense, aphanitic limestones with argillaceous dolostone interbeds. Uses: Quarried at Kirkfield, Victoria County, and Uthoff for crushed stone. The product is generally fresh and compact with good cubic-shaped factor, low clay content, low absorption, and low soundness losses. Smooth particle surfaces may cause adhesion problems for asphalt. There is some alkali reactivity in a few of the layers.

LOCKPORT AND AMABEL FORMATIONS (MIDDLE SILURIAN)

Composition: Amabel Formation (Waterdown to the Bruce Peninsula): massive, fine crystalline dolostone, with reef facies dolostone near Georgetown. Lockport Formation (lateral facies equivalent to the Amabel Formation from Watertown to Niagara Falls): thin- to massive-bedded, fine- to medium-grained dolostone. Thickness: Amabel Formation: maximum observed thickness of 84 feet (26 m). Lockport Formation: up to 130 feet (40 m). Uses: The Lockport and Amabel Formations have been used to produce lime, crushed stone, and building stone throughout their area of occurrence, and are a valuable aggregate resource. Los Angeles Abrasion Test: 21-35% loss; Soundness Test: 2.0% loss; Absorption: 0.4-1.6%.

ONONDAGA FORMATION (MIDDLE DEVONIAN)

(Equivalent to the Detroit River Group, with a textural change) Composition: Edgecliffe Member: medium-bedded, fine- to medium-grained, dark grey cherty limestone with an estimated thickness of 25 to 30 feet (8 to 9 m). Clarence Member: massive-bedded, dark grey brown, fine-grained, very cherty limestone having an estimated thickness of 26 feet (8 m). Moorehouse Member: medium-bedded, dark grey brown or purplish brown, fine- to coarse-grained, variably cherty limestone with an estimated thickness of 15 to 25 feet (5 to 8 m). Uses: Quarried for crushed stone on the Niagara Peninsula at Welland and Port Colborne. High chert content makes much of the material unsuitable for concrete aggregate.

OTTAWA FORMATION (MIDDLE ORDOVICIAN)

Composition: Lower Phase (Lowville and Pamela Beds): shale, some sandstone and dolostone. Thickness: 100 feet (30 m). Middle Phase (Hull, Rockland, and Leray Beds): pure, thick-bedded, crystalline limestone. Thickness: 150 feet (46 m) near Ottawa. Upper Phase (Cobourg and Sherman Falls Beds): pure and impure crystalline limestone with few to numerous shaly partings, 450 to 475 feet (137 to 145 m) thick near Ottawa. Uses: The Leray, Rockland, and Hull Beds have been quarried extensively for crushed stone and for building stone. In addition, the Hull Beds are an excellent source of lime for cement production and agricultural uses.

OXFORD FORMATION (LOWER ORDOVICIAN)

Composition: Medium- to thick-bedded, grey dolostone, with some shaly partings. Thickness: 240 feet (73 m). Uses: Quarried for crushed stone (road and concrete aggregate) at Ottawa, Brockville, and Smiths Falls.

BEDROCK SUITABLE FOR LIME PRODUCTION AND OTHER CHEMICAL USES.

DETROIT RIVER GROUP (MIDDLE DEVONIAN)

(Equivalent to the Onondaga Formation in the Niagara Peninsula, with a textural change). Composition: Near Beachville, the group consists of medium- to micro-crystalline, medium-bedded, high purity limestone. It grades northwards near St. Marys to soft, evenly bedded, fine-grained dolostone with bituminous laminae. Massive, porous, reef facies material also occurs to the north (Formosa Reef Limestone). Thickness: 100 feet (30 m) at Beachville, 350 feet (107 m) at Clinton. Uses: The most important

source of high purity limestone in Ontario is the Lucas Formation of the Detroit River Group at Beachville. Detroit River limestone produces 80% of Ontario's cement. Its dolomitic reefal facies is also important for lime production to the north. It is generally unsuitable for crushed stone. The Anderdon Member of the Lucas formation is quarried at Amherstburg for crushed stone.

GRENVILLE MARBLE (PRECAMBRIAN)

Composition: Recrystallized white limestone and dolostone, fine- to coarse-grained, usually of high chemical purity. Uses: Lime production, but also in small amounts for terrazo chips, poultry grit, decorative stone, and building stone.

GUELPH FORMATION (MIDDLE SILURIAN)

Composition: Aphanitic- to medium-crystalline, thick-bedded, soft, porous dolostone, characterized in places by extensive vuggy, porous reefal facies dolostone of high chemical purity. The Guelph Formation and the underlying Amabel Formation have a combined thickness of 200 feet (61 m) on the Niagara Peninsula and more than 400 feet (122 m) on the Bruce Peninsula. Uses: The main use is for dolomitic lime in the construction industry. It is quarried at Glen Christie and Guelph.

LINDSAY FORMATION (MIDDLE ORDOVICIAN)

Composition: Lower Member: fine-crystalline, rubbly, nodular, weathering limestone. Upper Member: grey calcareous claystone with shaly partings and bioclastic layers. The rock is "soft" and weathers to rubble. Both members are characterized by low dolomite content and by numerous clayey partings. Uses: Quarried at Picton, Ogden Point, Colborne, and Bowmanville for lime. It is generally unsuitable for crushed stone, concrete aggregate, or granular base course.

VERULAM FORMATION (MIDDLE ORDOVICIAN)

Composition: Fossiliferous, pure to argillaceous limestone and interbedded calcareous shale. The rock is not resistant to erosion and commonly weathers to rubble. Thickness: 200-300 feet (61-91 m). Uses: Quarried at Picton, Ogden Point, and Mara Township for lime. It is unsuitable for crushed stone due to clay impurities and many clayey interbeds, low abrasion resistance. High soundness losses and poor freeze-thaw resistance.

BEDROCK SUITABLE FOR BRICK AND TILE MANUFACTURE

GEORGIAN BAY FORMATION (UPPER ORDOVICIAN)

(Formerly known as the Meaford-Dundas and Blue Mountain shales in the Toronto and Bruce Peninsula areas). Composition: Soft, fissile, blue grey shale with limey or sandy lenses in a few places. Thickness: 640 feet (195 m) at Toronto. Uses: Five producers in Metro Toronto and Cooksville produce brick and structural tile (Guillet 1967). Lightweight aggregate is also produced at Streetsville by heat expansion of the shale.

HAMILTON GROUP (MIDDLE DEVONIAN)

Composition: Grey shale with interbeds of crystalline and cherty limestone. The Group has six formations. Only the Arkona is of commercial value. It is a soft, light grey, calcareous shale which is plastic and easily worked when wet. Thickness: 80 to 300 feet (24 to 91 m). Uses: The Arkona Formation is extracted at Thedford and near Arkona for production of drainage tile and brick.

QUEENSTON FORMATION (UPPER ORDOVICIAN)

Composition: Red, thin- to thick-bedded, sandy to argillaceous shale with green mottling and banding. Thickness: 400 to 500 feet (122 to 152 m). Uses: There are 12 large shale quarries developed in the Queenston Formation in the Toronto-Hamilton region and one at Russell, near Ottawa (Guillet 1967). All produce brick for construction. The Queenston Formation is the most important source material for brick manufacture in the Province.

BEDROCK SUITABLE FOR OTHER INDUSTRIAL PRODUCTS

NEPEAN (POTSDAM) FORMATION (CAMBRO-ORDOVICIAN)

Composition: Creamy, coarse-grained, silica sandstone. Uses: Quarried throughout its area of outcrop for building stone, decorative stone, abrasives, and for glass making.

SALINA FORMATION (UPPER SILURIAN)

Composition: Grey and red shale, brown dolomite, and, in places, salt, anhydrite, and gypsum. The formation consists predominantly of evaporite deposits with up to eight members identified. Uses: Gypsum is mined at Hagersville, Caledonia, and Drumbo. Salt is mined at Goderich and is produced from brine wells at Amherstburg, Windsor, and Sarnia.

WHITBY FORMATION (UPPER ORDOVICIAN)

(Formerly known as Collingwood Shale near Toronto). Composition: Brown to black fissile shale. Uses: Quarried at Bowmanville for use in cement production. Testing indicates that the Whitby Formation may produce satisfactory lightweight expanded aggregate.

DEPOSIT SYMBOL

Deposits are identified by gravel content, thickness class, deposit type and quality indicators. Gravel content is expressed as percentage of crushable material. Classes are based on potential aggregate tonnage per acre and are designated numerically. Type refers to geologic origin. Quality modifiers indicate variations in grain size distribution and lithology.

Gravel Content	Thickness Class	Geological Type
		Quality Indicators

Gravel Content

G	Greater than 35% gravel.
S	Less than 35% gravel.
C	Clay resource area (no resource tonnage estimate has been prepared, see text).

Thickness Class

Class	Average Thickness in feet (metres)	Tons per acre (Tonnes per hectare)
1	greater than 20 (> 6)	greater than 50,000 (>112 000)
2	10-20 (3-6)	25,000-50,000 (56 000 - 112 000)
3	5-10 (1.5-3)	12,500-25,000 (28 000 - 56 000)
4	less than 5 (< 1.5)	less than 12,500 (<28 000)

Geological Type

IC	Undifferentiated Ice Contact Stratified Drift	OW	Outwash
ICT	Ice-Contact Terrace	LB	Lacustrine Beach
K	Kame	LP	Lacustrine Plain
E	Esker	LD	Lacustrine Delta
EM	End Moraine	AL	Older Alluvium
		WD	Windblown Forms

(see Appendix C for descriptions of Geological Types.)

Quality Indicators

	If blank, no known limitations present
C	Clay and/or silt (fines) present in objectionable quantities
L	Deleterious lithologies present
O	Oversize particles or fragments present in objectionable quantities

SOURCES OF INFORMATION

Base map by Surveys and Mapping Branch, Ontario Ministry of Natural Resources.
Licence data from District and Regional Offices, Ontario Ministry of Natural Resources.
Aggregate suitability data from the Engineering Materials Office Ontario Ministry of Transportation and Communications.
Selected drilling data from the Ontario Ministry of the Environment and the Petroleum Resources Section, Ontario Ministry of Natural Resources.

Geology by: P. F. Karrow, 1977



Ministry of Natural Resources
Ontario

Hon. Alan W. Pope
Minister

W.T. Foster
Deputy Minister

ONTARIO GEOLOGICAL SURVEY
AGGREGATE RESOURCES INVENTORY

BIDDULPH TOWNSHIP

MIDDLESEX COUNTY

MAP 1
DISTRIBUTION OF SAND AND GRAVEL DEPOSITS

Scale: 1:50 000

Mile 1 0 1 Mile

Metres 1000 0 1 Kilometre

NTS Reference: **40 P/3, 40 P/6**

© OMNR-OGS 1982



SYMBOLS
(Some symbols may not apply to this map)

Geological and aggregate thickness boundary. Shading indicates deposit area.

Municipal boundary.

S 1 IC C-I Deposit symbol, see adjacent column.

Quality Indicators

	If blank, no known limitations present
C	Clay and/or silt (fines) present in objectionable quantities
L	Deleterious lithologies present
O	Oversize particles or fragments present in objectionable quantities

SOURCES OF INFORMATION

Base map by Surveys and Mapping Branch, Ontario Ministry of Natural Resources.
Licence data from District and Regional Offices, Ontario Ministry of Natural Resources.
Aggregate suitability data from the Engineering Materials Office Ontario Ministry of Transportation and Communications.
Selected drilling data from the Ontario Ministry of the Environment and the Petroleum Resources Section, Ontario Ministry of Natural Resources.

Geology by: P. F. Karrow, 1977
E.V. Sado and U.J. Vagners, 1975

Compilation and drafting by: Staff of the Aggregate Assessment Office.

Issued 1982.

This map is published with the permission of E.G. Pye, Director, Ontario Geological Survey.

This paper is to accompany O.G.S. Aggregate Resources Inventory Paper 57.



BIDDULPH



SYMBOLS

(Some symbols may not apply to this map)

- Geological and aggregate thickness boundary. Shading indicates deposit area.
- Municipal boundary.
- S1 IC C-L — Deposit symbol see adjacent column.
- 3 — Licenced property boundary. Property number see Table 2
- 4 — Unlicenced sand or gravel pit*; Property number: see Table 2 *Abandoned pit or wayside pit operating on demand under authority of a permit.
- O 27 — Selected drilling location indicating thickness of overburden overlying reported thickness of granular materials (in feet). (Note: S - sand, G - gravel, T - till)

USBORNE TP
BIDDULPH TP
PERTH CO.
MIDDLESEX CO.
BIDDULPH TP
McGILLIVRAY TP
BLANSHARD TP
BIDDULPH TP
Whalen Corners
Mooresville
Granton
Lucan
Clandeboye
CANADIAN NATIONAL
Ausable River
Dutch Creek
Cemetery
Trans
Poultry farm
Dugouts
Orchard
Sports Track
Sewage
Arena
Fur Farm
Plant
Elevator
Observatory
Dugout
Silo
Ditch
BM 980
BM 1030
910
865
956
958
964
909
977
I
II
III
IV
V
VI
VII
VIII
IX
X
XI
XII
XIII
XIV
XV
XVI
XVII
XVIII
XIX
XX
N

Ontario

Ministry of Natural Resources

Hon. Alan W. Pope
Minister

W.T. Foster
Deputy Minister

ONTARIO GEOLOGICAL SURVEY
AGGREGATE RESOURCES INVENTORY

BIDDULPH TOWNSHIP
MIDDLESEX COUNTY

MAP 2
SELECTED SAND AND GRAVEL RESOURCE AREAS

Scale: 1:50 000

Mile 1 0 1 Mile
Metres 1000 0 1 Kilometre

NTS Reference: **40 P/3, 40 P/6**

© OMNR-OGS 1982



SYMBOLS
(Some symbols may not apply to this map)

- Geological and aggregate thickness boundary.
- Municipal boundary
- Selected sand and gravel resource area; Primary significance; Deposit number: see Table 3.
- Selected sand and gravel resource area; Secondary significance.
- Selected sand and gravel resource area; Tertiary significance.
- 2 Licenced property boundary; Property number see Table 2.
- Unlicenced sand or gravel pit; Property number see Table 2

Mooresville
BM 980
Ditch
Poultry Farm
Ausable River
Plant
Orchard
Sports Track
Sewage
Dugouts
Granton
BM 999
BLANSHARD TP
BIDDULPH TP
Site
Dugout
Observatory
Claudeboye
Fur Farm
Arena
Sports Track
CANADIAN NATIONAL
BM 1030
Lucan
Elevator
Sports Track
Abattoir
Sports Tracks
Meadow Creek Ditch
Dugout
Orchard
BM 965
Elginfield
Trans Sta
Gravel Pit
Brick and Tile Yard
Sports Track
Poultry Farm
BIDDULPH TP
LONDON TP
Dugout
BIDDULPH

BIDDULPH

Mile 1 0 1 Mile

Metres 1000 0 1 Kilometre

NTS Reference: **40 P/3, 40 P/6**

© OMNR-OGS 1982



SYMBOLS

(Some symbols may not apply to this map)

- Geological and aggregate thickness boundary.
- Municipal boundary.
- Selected sand and gravel resource area; Primary significance; Deposit number: see Table 3.
- Selected sand and gravel resource area; Secondary significance.
- Selected sand and gravel resource area; Tertiary significance.
- Licenced property boundary; Property number: see Table 2.
- Unlicenced sand or gravel pit*; Property number: see Table 2. *Abandoned pit or wayside pit operating on demand under authority of a permit.

SOURCES OF INFORMATION

Base map by Surveys and Mapping Branch, Ontario Ministry of Natural Resources.
Licence data from District and Regional Offices, Ontario Ministry of Natural Resources.
Aggregate suitability data from the Engineering Materials Office, Ontario Ministry of Transportation and Communications.
Selected drilling data from the Ontario Ministry of the Environment and the Petroleum Resources Section, Ontario Ministry of Natural Resources.

Geology by: P. F. Karrow, 1977
E.V. Sado and U.J. Vagners, 1975

Compilation and drafting by: Staff of the Aggregate Assessment Office.

Issued 1982.

This map is published with the permission of E.G. Pye, Director, Ontario Geological Survey.

This map is to accompany O.G.S. Aggregate Resources Inventory Paper 57.

SYMBOLS

(Some symbols may not apply to this map)

- Geological boundary.
- Municipal boundary.
- 25 — Drift thickness contour line (25-foot (8 m) interval).
- x — Isolated bedrock outcrop.
- Bedrock within 3 feet (1 m) of surface: see Table 4.
- Bedrock covered by 3 to 25 feet (1 m to 8 m) of overburden: see Table 4.
- Bedrock covered by 25 to 50 feet (8 m to 15 m) of overburden: see Table 4.
- (1) — Selected bedrock resource area; Deposit number: see Table 6.
- Q3 — Licenced quarry boundary; Property number: see Table 5.
- ●Q4 — Unlicenced quarry*; Property number: see Table 5.
  *Abandoned quarry or wayside quarry operating on demand under authority of a permit.
- O 27 — Selected drilling location indicating reported depth to bedrock (in feet).

SOURCES OF INFORMATION

Base map by Surveys and Mapping Branch, Ontario Ministry of Natural Resources.
Licence data from District and Regional Offices, Ontario Ministry of Natural Resources.
Aggregate suitability data from the Engineering Materials Office, Ontario Ministry of Transportation and Communications.
Selected drilling data from the Ontario Ministry of the Environment and the Petroleum Resources Section, Ontario Ministry of Natural Resources.

Geology by: P. F. Karrow, 1965
P. F. Karrow and A. J. Ferguson, 1975
E. V. Sado and D. Jones, 1980
B. V. Sanford, 1969

Compilation and drafting by: Staff of the Aggregate Assessment Office.

Issued 1982

This map is published with the permission of E.G. Pye, Director, Ontario Geological Survey.

This map is to accompany O.G.S. Aggregate Resources Inventory Paper 57.



Ministry of Natural Resources

Ontario

Hon. Alan W. Pope
Minister

W.T. Foster
Deputy Minister

ONTARIO GEOLOGICAL SURVEY
AGGREGATE RESOURCES INVENTORY

BIDDULPH TOWNSHIP
MIDDLESEX COUNTY

MAP 3
BEDROCK RESOURCES

Scale: 1:50 000

Mile 1 0 1 Mile

Metres 1000 0 1 Kilometre

NTS Reference: **40 P/3, 40 P/6**

© OMNR-OGS 1982



LEGEND

PALEOZOIC

DEVONIAN

MIDDLE DEVONIAN

DUNDEE FORMATION
Limestone

Issued 1982.

This map is published with the permission of E.G. Pye, Director, Ontario Geological Survey.

This map is to accompany O.G.S. Aggregate Resources Inventory Paper 57.

LEGEND

PALEOZOIC

DEVONIAN

MIDDLE DEVONIAN

DUNDEE FORMATION
Limestone

BIDGULPH